



## PRODUCT SUBMITTAL INFORMATION

### THERMAL GROUT LITE 45

PO Box 255 • Elkton, SD 57026 • (605) 542-7391 • Fax (605) 542-1303  
PO Box 150 • Bowie, TX 76230 • (940) 872-8097 • Fax (940) 872-3678

April, 2007

**THERMAL GROUT LITE** is a unique bentonite-based two-part, field mixed, high to extreme-high solids material that can be mixed to meet a range of thermal conductivity's from 0.45 to 1.00 Btu/hr-ft-°F. It has been specifically developed for closed-loop ground-coupled heat pump applications where thermal conductivity in the vertical bore column is critical to system performance. This product is certified by the National Sanitation Foundation International to ANSI/NSF Standard 60, *Drinking Water Treatment Chemical - Health Effects*. **THERMAL GROUT LITE** contains no chemical polymers or organic matter.

When supplied by GeoPro, Inc. and mixed according to the following specifications, **THERMAL GROUT LITE** will yield a bentonite-based grouting material with a minimum thermal conductivity of 0.45 Btu/hr-ft-°F as determined when tested in accordance to ASTM D-5334, "Standard Test Method for Determination of Thermal Conductivity of Soils and Soft Rock by Thermal Needle Probe Procedure". The specific mixture described in this document is called **THERMAL GROUT LITE 45**.

#### **MIXING INSTRUCTIONS for THERMAL GROUT LITE 45** (per each unit):

***The following information is considered proprietary and confidential and should not be shared with any competing company to GeoPro, Inc.***

1. Place 14.0 gallons of fresh water in a conventional paddle mixing tank.
2. Start mixer and add one 50 lb bag of *Bentonite Base (Part I - Thermal Grout Lite)* then continue to mix for 1 to 2 minutes to obtain a consistent mixture.
3. Pump with a positive displacement pump (piston pump recommended) through a 1-1/4" inside diameter tremie pipe at a rate of 5 to 15 gallons per minute.

When mixed according to these instructions, each unit will yield 17.0 gallons with a density of 9.81 lb/gal. The total solids content will be 30.0% and will have a linear shrinkage potential of less than 11%. The amount of thermal enhancement compound contained in this mixture will equate to 0.0% of this product by weight.

The permeability of this mixture will be less than  $6.8 \times 10^{-8}$  cm/sec, which has been verified by an independent testing laboratory using ASTM D-5084, "Measurement of Hydraulic Conductivity of Saturated Porous Materials using a Flexible Wall Permeameter, Method C - test with increasing tailwater level", and is below most States regulations and the U.S. Environmental Protection Agency's maximum recommendations of  $1 \times 10^{-7}$  cm/sec. Copies of the independent lab reports are available upon request.

#### **FIELD QUALITY CONTROL for THERMAL GROUT LITE 45:**

GeoPro, Inc. strongly recommends that a field quality control process be employed when using any thermally-enhanced grouting material. Therefore, GeoPro will supply, at no charge, three sample containers with return cartons per commercial project using **THERMAL GROUT LITE 45**. Through the course of the project, it is recommended that at least three sample specimens be taken of the mixed grouting material. The recommended frequency would be as follows: once at the beginning of the installation; once approximately one-third through the installation; and once approximately two-thirds through the installation. Each time GeoPro receives the sample, an analysis will be performed in accordance to ASTM D-5334 to verify the specified thermal performance of the sample with a written report being sent immediately to the entity requesting the analysis.

For each project, additional sample containers can be supplied and analyses performed for a modest fee.

Allan Skouby, Director of Sales and Marketing  
**GeoPro, Inc.**